

ESTOPLAST EP 2030GY39

Polybutylene Terephthalate

Ester Industries Ltd.

Message:

Polybutylene Terephthalate - Glass Fiber Reinforcement, 30%

Automotive: Plug and socket Connectors, Head/Tail Lamp Housings

Electrical & Electronic: Connectors, Switch Parts, Electrical Enclosure

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	demoulding		
Features	Good demoulding performance		
Uses	Plug		
	Electrical/Electronic Applications		
	Switch		
	Connector		
	Application in Automobile Field		
	Shell		
RoHS Compliance	RoHS compliance		
Appearance	Brown		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm³	ASTM D792
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	105	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Strength	170	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	50	J/m	ASTM D256A
Unnotched Izod Impact (23°C)	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	220	°C	ASTM D648
1.8 MPa, not annealed	200	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257

Comparative Tracking Index (CTI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	HB		UL 94
1.5 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	235 - 240	°C	
Middle Temperature	250 - 260	°C	
Nozzle Temperature	250 - 260	°C	
Processing (Melt) Temp	240 - 250	°C	
Mold Temperature	100 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

