# Karina IVORY PVC COMP -E 813-35/

# 1-Y-SN-ERYB

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

#### Message:

TIN STABILIZED PVC COMPOUND RECOMMENDED FOR EXTRUSION OF INTERIOR FURNISHING BOARDS AND PROFILES - SPECIALLY DEVELOPED FOR TEKNAFORM CANADA.

General Information			
Additive	Tin Stabilizer		
Uses	Profiles		
Appearance	lvory		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	1.33 to 1.39	g/cm³	ASTM D792
Color a	-3.03 to -0.0300		ME 12
Color b	4.43 to 7.43		ME 12
Color L	80.6 to 83.6		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	78 to 82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 39.2	МРа	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

