

XYLEX™ X8210 resin

Polycarbonate + Polyester
SABIC Innovative Plastics Europe

Message:
PC+POLYESTER alloy. Unreinforced, transparent, impact modified for low temperature ductility

General Information			
Additive	Impact modifier		
Features	Impact modification ductility		
Appearance	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.16	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
265°C/2.16 kg	10	g/10 min	ASTM D1238
300°C/1.2 kg	14	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)			ISO 1133
265°C/2.16 kg	10.0	cm ³ /10min	ISO 1133
300°C/1.2 kg	13.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.50 - 0.80	%	Internal method
Transverse flow: 3.20mm	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.37	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1480	MPa	ASTM D638
--	1500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	43.0	MPa	ASTM D638
Yield	45.0	MPa	ISO 527-2/50
Fracture ³	46.0	MPa	ASTM D638
Fracture	45.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.0	%	ASTM D638

Yield	4.6	%	ISO 527-2/50
Fracture ⁵	150	%	ASTM D638
Fracture	> 150	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	1600	MPa	ASTM D790
-- ⁷	1600	MPa	ISO 178
Flexural Stress			
--	58.0	MPa	ISO 178
Yield, 50.0mm span ⁸	65.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	71	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	200	J/m	ASTM D256
-20°C	640	J/m	ASTM D256
23°C	800	J/m	ASTM D256
-30°C ¹⁰	11	kJ/m ²	ISO 180/1A
-10°C ¹¹	30	kJ/m ²	ISO 180/1A
23°C ¹²	45	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	81.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	79.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	75.0	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹³	82.0	°C	ISO 75-2/Ae
1.8 MPa, unannealed, 64.0mm span ¹⁴	81.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	97.0	°C	ASTM D1525, ISO 306/B120 12 ¹⁵
--	92.0	°C	ISO 306/B50
Linear thermal expansion coefficient			
Flow: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	8.3E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	8.9E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (2540 μm)	85.0	%	ASTM D1003
Haze (2540 μm)	4.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	65.6 - 76.7	°C	
Drying Time	3.0 - 5.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	

Suggested Shot Size	40 - 80	%
Rear Temperature	238 - 249	°C
Middle Temperature	238 - 260	°C
Front Temperature	243 - 266	°C
Nozzle Temperature	243 - 266	°C
Processing (Melt) Temp	243 - 266	°C
Mold Temperature	43.3 - 60.0	°C
Back Pressure	0.172 - 0.517	MPa
Screw Speed	20 - 100	rpm
Vent Depth	0.013 - 0.020	mm

NOTE

1.	50 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4
13.	120*10*4 mm
14.	80*10*4 mm
15.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT