

NORYL™ FE1630PW resin

Polyphenylene Ether + PS

SABIC Innovative Plastics Europe

Message:

Noryl* FE1630PW Polyphenylene Oxide (PPO) + Polystyrene (PS) resin is a 30% Glass Reinforced, injection moldable grade with improved hydrolytic stability; this grade has been developed for fluid engineering applications. Noryl* FE1630PW has been certified for potable water applications up to 85C in Europe and North America in limited colours

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Uses	Potable water application		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	9.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/10.0 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.10 - 0.30	%	Internal method
Transverse flow: 3.20mm	0.20 - 0.50	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.20	%	ISO 62
Equilibrium, 23°C, 50% RH	0.060	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	240	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	9580	MPa	ASTM D638
--	9600	MPa	ISO 527-2/1
Tensile Strength			
Fracture ²	134	MPa	ASTM D638
Fracture	133	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ³	2.4	%	ASTM D638
Fracture	2.5	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁴	7760	MPa	ASTM D790
-- ⁵	8120	MPa	ISO 178
Flexural Stress	192	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	65.0	mg	Internal method

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶			ISO 179/1eA
-30°C	9.0	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ⁷			ISO 179/1eU
-30°C	30	kJ/m ²	ISO 179/1eU
23°C	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
-30°C	75	J/m	ASTM D256
23°C	85	J/m	ASTM D256
-30°C ⁸	7.0	kJ/m ²	ISO 180/1A
23°C ⁹	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	470	J/m	ASTM D4812
23°C	510	J/m	ASTM D4812
-30°C ¹⁰	30	kJ/m ²	ISO 180/1U
23°C ¹¹	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 100 mm span ¹²	150	°C	ISO 75-2/Be
1.8 MPa, unannealed, 3.20mm	145	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹³	145	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	165	°C	ISO 306/A50
--	154	°C	ISO 306/B50
--	158	°C	ISO 306/B120
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	100 - 120	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	250 - 270	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 300	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80.0 - 120	°C	
NOTE			
1.	5.0 mm/min		

2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	1.3 mm/min
5.	2.0 mm/min
6.	80*10*4 sp=62mm
7.	80*10*4 sp=62mm
8.	80*10*4
9.	80*10*4
10.	80*10*4
11.	80*10*4
12.	120*10*4 mm
13.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

