

LNP™ STAT-KON™ EX01696C compound

Polyether Imide

SABIC Innovative Plastics

Message:

LNP STAT-KON EX01696C is a compound based on Polyetherimide resin containing Proprietary Filler(s). Added features of this material include: Electrically Conductive, Clean Compounding System.

Also known as: LNP* STAT-KON* Compound PDX-E-01696 CCS

Product reorder name: EX01696C

General Information			
Filler / Reinforcement	Proprietary packing		
Features	Low (to None) Ion Content		
	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3700	MPa	ASTM D638
Tensile Strength (Break)	94.5	MPa	ASTM D638
Tensile Elongation (Break)	3.6	%	ASTM D638
Flexural Modulus	3630	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256
Unnotched Izod Impact (23°C)	480	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+6 - 1.0E+8	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121 - 149	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 - 354	°C	
Middle Temperature	354 - 366	°C	
Front Temperature	366 - 377	°C	
Processing (Melt) Temp	360 - 366	°C	
Mold Temperature	121 - 149	°C	
Back Pressure	0.344 - 0.689	MPa	
Screw Speed	60 - 100	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

