

RTP 2799 S X 118623 B

Styrene Ethylene Butylene Styrene Block Copolymer

RTP Company

Message:

EMI/RFI Shielding

General Information			
Features	Electromagnetic shielding (EMI)		
	Radio frequency shielding (RFI)		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm ³	ASTM D792
Moisture Content		%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	55		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain, 3.18 mm)	1.97	MPa	ASTM D412
Tensile Strength ² (Break, 3.20 mm)	2.21	MPa	ASTM D412
Tensile Elongation ³ (Break)	320	%	ASTM D412
Tear Strength ⁴	19.3	kN/m	ASTM D624
Compression Set ⁵			ASTM D395B
23°C, 22 hr	12	%	ASTM D395B
70°C, 22 hr	64	%	ASTM D395B
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	< 1.0	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 - 3.0	hr	
Processing (Melt) Temp	204	°C	
Mold Temperature	21.1 - 60.0	°C	
Injection instructions			
Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.			
NOTE			
1.	Mouth die C, 510mm/min		
2.	C mold, 500 mm/min		
3.	Mouth die C, 500 mm/min		
4.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

