

Panlite® LN-3010RM

Polycarbonate

TEIJIN LIMITED

Message:

High light reflection grade, Anti-environmental pollution type (Non-bromine/Non-phosphor type), Flame resistant grade

General Information			
UL YellowCard	E50075-241814	E244324-101516716	
Features	Flame Retardant		
	High Reflectivity		
Uses	LEDs		
	Lighting Applications		
	Reflectors		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.40 to 0.60	%	
Flow : 4.00 mm	0.40 to 0.60	%	
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2650	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	60.0	MPa	
Break	54.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	100	%	
Flexural Modulus ¹	2430	MPa	ISO 178
Flexural Stress ²	92.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	12	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	134	°C	ISO 75-2/B

1.8 MPa, Unannealed	125	°C	ISO 75-2/A
Vicat Softening Temperature	138	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
RTI Elec (1.50 mm)	80.0	°C	UL 746
RTI Imp (1.50 mm)	80.0	°C	UL 746
RTI Str (1.50 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength ³	32	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.40		
1 MHz	3.40		
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating ⁴			UL 94
0.400 mm	V-2		
1.60 mm	V-0		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	short time test		
4.	white		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT