

Jam PE 36XF6

High Density Polyethylene

Jam Petrochemical Company

Message:

Jam PE 36XF6 is a High Density Polyethylene product. It is available in Africa & Middle East. Typical application: Straps/Ropes.

General Information			
Uses	Rope		
Physical	Nominal Value	Unit	Test Method
Density	0.935 to 0.937	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50 to 0.70	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation ¹ (Break, 0.0250 mm)	> 23	%	ASTM D2101
Additional Information	Nominal Value	Unit	Test Method
Tenacity of Fibers - at Break			ASTM D2101
25.0 µm ²	5.80	g/denier	
25.0 µm ³	> 5.40	g/denier	
NOTE			
1.	Blown Film		
2.	Blown Film, 3500 denier strap,stretch ratio 1:8		
3.	Blown Film, 480 denier monofilament , stretch ratio 1:8.3		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT