

ELASTOSIL® R plus 4846/30

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Connectors, Automotive & Transportation

Molded Parts, Automotive, Plastics and Rubber Processing

Molded Parts, Technical, Plastics and Rubber Processing

Molded Seals, Plastics and Rubber Processing

General Information	
Features	Self Lubricating
Uses	Automotive Applications
	Automotive Under the Hood
	Gaskets
	Seals
Processing Method	Compression Molding
	Press Molding

Uncured Properties	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	DIN 53479
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	30		DIN 53505
Tensile Strength	10.0	MPa	DIN 53504
Tensile Elongation at Break	1000	%	DIN 53504
Compression Set	40	%	DIN ISO 815-B
Tear Strength	32.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT