

# Buna® EP T 6250

Ethylene Propylene Diene Terpolymer  
LANXESS Corporation

Message:

Ethylene-propylene-diene rubber (EPDM), with ethylidene norbornene (ENB) as diene; amorphous; medium viscosity.

| General Information                 |                  |                   |             |
|-------------------------------------|------------------|-------------------|-------------|
| Features                            | amorphous        |                   |             |
|                                     | Medium viscosity |                   |             |
| Forms                               | bag              |                   |             |
| Physical                            | Nominal Value    | Unit              | Test Method |
| Specific Gravity                    | 0.858            | g/cm <sup>3</sup> | ASTM D792   |
| Mooney Viscosity (ML 1+4, 125°C)    | 50 - 60          | MU                | ASTM D1646  |
| Ethylene Content                    | 59.0 - 65.0      | wt%               | ASTM D3900  |
| Ethylidene Norbornene (ENB) Content | 1.9 - 2.7        | wt%               | ASTM D6047  |
| Additional Information              |                  |                   |             |

Total Ash, ISO 247/ASTM D5667: <0.5%Stabilizer: Non-stainingVolatile Matter, ISO 248/ASTM D5668: <0.75 wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

