

SEQUEL® 1514-UV RXF AB

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Sequel 1514-UV RXF AB thermoplastic polyolefin material exhibits significantly greater mar resistance than conventional TPOs. Sequel 1514-UV RXF AB polyolefin is typically used for automotive applications that demand low warpage and low CLTE, along with excellent scratch and mar resistance.

General Information		
Features	Low CLTE	
	Low warpage	
	Scratch resistance	
Uses	Application in Automobile Field	
	Automotive exterior parts	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density (23°C)	0.980	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min
Mechanical	Nominal Value	Unit
Tensile Strength ¹ (Yield, 23°C)	23.8	MPa
Flexural Modulus ² (23°C)	1650	MPa
Impact	Nominal Value	Unit
Notched Izod Impact (23°C)	240	J/m
NOTE		
1.	50 mm/min	
2.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT