

# Hypro® PP-CP 20/10

Polypropylene Impact Copolymer

Entec Polymers

## Message:

This product is intended for general purpose injection molding applications including flooring, automotive, appliance, lawn & garden and industrial application.

General Information			
Features	General Purpose		
	Impact Copolymer		
Uses	Appliances		
	Automotive Applications		
	Flooring		
	General Purpose		
	Industrial Applications		
	Lawn and Garden Equipment		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	24.0	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	6.0	%	ASTM D638
Flexural Modulus - 1% Secant <sup>1</sup> (23°C)	1210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	> 540	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	182 to 216	°C	
Middle Temperature	193 to 238	°C	
Front Temperature	204 to 249	°C	
Nozzle Temperature	193 to 238	°C	
Processing (Melt) Temp	204 to 249	°C	

Mold Temperature	21.1 to 48.9	°C
Injection Pressure	3.45 to 10.3	MPa
NOTE		
1.	1.3 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

