Hostacom TRC 399N G21373

Polypropylene Copolymer LyondellBasell Industries

Message:

Hostacom TRC 399N G21373 is a 14% talc filled PP copolymer, with excellent impact/stiffness balance, excellent flowability and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G21373 color version.

For regulatory compliance information, see Hostacom TRC 399N G21373 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 14% filler by weight		
Features	Rigid, good		
	Copolymer		
	Impact resistance, good		
	Good UV resistance		
	Workability, good		
	Good liquidity		
	Good appearance		
Uses	Application in Automobile Field		
	Car dashboard		
	A 2111 1		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.00	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	23	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ¹ (23°C)	1800	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	5.0	kJ/m²	ISO 180/1A
23°C	38	kJ/m²	ISO 180/1A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

