

NuSil FS-3730

Silicone

NuSil Technology

Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

- Fuel Resistance
- Static Dissipation and Electrically Conductive Silicones
- Ice-Phobic Coatings
- General Purpose: Adhesives and Sealants
- Comment: Available in Gray/Black/Translucent

| General Information | | |
|---------------------------------|-------------------------|-------------------|
| Features | Electrically Conductive | |
| | Fuel Resistant | |
| Uses | Adhesives | |
| | Aircraft Applications | |
| | Sealants | |
| Thermoset | Nominal Value | Unit |
| Tack Free Time | 30.0 | min |
| Cure System | Acetoxxy | |
| Operating Temperature | -50 to 200 | °C |
| Uncured Properties | Nominal Value | Unit |
| Color | White | |
| Density | 1.40 | g/cm ³ |
| Curing Time (23°C) | 72 | hr |
| Cured Properties | Nominal Value | Unit |
| Shore Hardness (Shore A) | 35 | |
| Lap Shear Strength ¹ | 2.62 | MPa |
| Tensile Strength | 5.86 | MPa |
| Tensile Elongation at Break | 430 | % |
| Tear Strength | 10.5 | kN/m |
| NOTE | | |
| 1. | Primed with SP-130 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

