

Petrothene® NA340212

Low Density Polyethylene

LyondellBasell Industries

Message:

Petrothene NA340 is a series of LDPE/EVA copolymer resins selected by customers for film applications that require clarity and good impact strength. Typical applications include heavy produce, textile, frozen food packaging and sealant films.

General Information	
Additive	High Antiblock
Features	Copolymer
	Food Contact Acceptable
	Good Impact Resistance
	High Antiblocking
	High Clarity
Uses	Film
	Food Packaging
	Packaging
Agency Ratings	FDA 21 CFR 177.1350
Forms	Pellets
Processing Method	Blown Film
	Film Extrusion

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Vinyl Acetate Content	4.0	wt%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	32	µm	
Secant Modulus			ASTM D882
1% Secant, MD : 32 µm, Blown Film	145	MPa	
1% Secant, TD : 32 µm, Blown Film	165	MPa	
Tensile Strength			ASTM D882
MD : Break, 32 µm, Blown Film	25.5	MPa	
TD : Break, 32 µm, Blown Film	21.4	MPa	
Tensile Elongation			ASTM D882
MD : Break, 32 µm, Blown Film	340	%	
TD : Break, 32 µm, Blown Film	500	%	
Dart Drop Impact (32 µm, Blown Film)	140	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922

MD : 32 μm, Blown Film	180	g	
TD : 32 μm, Blown Film	250	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	95.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 31.8 μm, Blown Film)	75		ASTM D2457
Haze (31.8 μm, Blown Film)	4.0	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	166 to 191	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

