

Lucky Enpla LGF3252F

Polybutylene Terephthalate

Lucky Enpla Co LTD

Message:

Lucky Enpla LGF3252F is a polybutene terephthalate (PBT) product, which contains a 25% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Lucky Enpla LGF3252F applications include electrical/electronic applications and the automotive industry.

Features include:

Flame Retardant

Hard

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight		
Features	Rigidity, high		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Connector		
	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 - 1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	118	MPa	ASTM D638
Flexural Modulus ²	7450	MPa	ASTM D790
Flexural Strength ³	177	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	74	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	207	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	220 - 240	°C	
Middle Temperature	240 - 260	°C	
Front Temperature	245 - 265	°C	
Nozzle Temperature	250 - 270	°C	
Mold Temperature	80.0 - 110	°C	
Back Pressure	0.490 - 2.94	MPa	

Screw Speed	30 - 60	rpm
Injection instructions		
Resin Temperature: 230-250°CInjection Pressure (1st Pressure): 700-1200 kg/cm ² Injection Pressure (2nd Pressure): 500-900 kg/cm ²		
NOTE		
1.	10 mm/min	
2.	3.0 mm/min	
3.	3.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

