

# LEXAN™ HFD1910 resin

Polycarbonate

SABIC Innovative Plastics

## Message:

55 MFR LEXAN High Flow Ductile Copolymer, Natural colors only

| General Information                        |                   |                        |                     |
|--------------------------------------------|-------------------|------------------------|---------------------|
| UL YellowCard                              | E45329-101013182  |                        |                     |
| Features                                   | Copolymer         |                        |                     |
|                                            | High liquidity    |                        |                     |
|                                            | ductility         |                        |                     |
| RoHS Compliance                            | RoHS compliance   |                        |                     |
| Appearance                                 | Natural color     |                        |                     |
| Processing Method                          | Injection molding |                        |                     |
| Physical                                   | Nominal Value     | Unit                   | Test Method         |
| Specific Gravity                           | 1.20              | g/cm <sup>3</sup>      | ASTM D792, ISO 1183 |
| Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)   | 55                | g/10 min               | ASTM D1238          |
| Melt Volume-Flow Rate (MVR) (300°C/1.2 kg) | 51.0              | cm <sup>3</sup> /10min | ISO 1133            |
| Molding Shrinkage - Flow (3.20 mm)         | 0.50 - 0.70       | %                      | Internal method     |
| Water Absorption                           |                   |                        | ISO 62              |
| Saturated, 23°C                            | 0.30              | %                      | ISO 62              |
| Equilibrium, 23°C, 50% RH                  | 0.15              | %                      | ISO 62              |
| Hardness                                   | Nominal Value     | Unit                   | Test Method         |
| Rockwell Hardness (R-Scale)                | 120               |                        | ASTM D785           |
| Mechanical                                 | Nominal Value     | Unit                   | Test Method         |
| Tensile Modulus                            |                   |                        |                     |
| -- <sup>1</sup>                            | 2300              | MPa                    | ASTM D638           |
| --                                         | 2200              | MPa                    | ISO 527-2/1         |
| Tensile Strength                           |                   |                        |                     |
| Yield <sup>2</sup>                         | 60.0              | MPa                    | ASTM D638           |
| Yield                                      | 61.0              | MPa                    | ISO 527-2/50        |
| Fracture <sup>3</sup>                      | 57.0              | MPa                    | ASTM D638           |
| Fracture                                   | 56.0              | MPa                    | ISO 527-2/50        |
| Tensile Elongation                         |                   |                        |                     |
| Yield <sup>4</sup>                         | 5.5               | %                      | ASTM D638           |
| Yield                                      | 6.0               | %                      | ISO 527-2/50        |
| Fracture <sup>5</sup>                      | 110               | %                      | ASTM D638           |
| Fracture                                   | 100               | %                      | ISO 527-2/50        |

|                                                |               |                   |                          |
|------------------------------------------------|---------------|-------------------|--------------------------|
| Flexural Modulus                               |               |                   |                          |
| 50.0mm span <sup>6</sup>                       | 2280          | MPa               | ASTM D790                |
| -- <sup>7</sup>                                | 2200          | MPa               | ISO 178                  |
| Flexural Stress                                |               |                   |                          |
| --                                             | 90.0          | MPa               | ISO 178                  |
| Yield, 50.0mm span <sup>8</sup>                | 100           | MPa               | ASTM D790                |
| Impact                                         | Nominal Value | Unit              | Test Method              |
| Charpy Notched Impact Strength <sup>9</sup>    |               |                   | ISO 179/1eA              |
| -30°C                                          | 11            | kJ/m <sup>2</sup> | ISO 179/1eA              |
| 23°C                                           | 60            | kJ/m <sup>2</sup> | ISO 179/1eA              |
| Charpy Unnotched Impact Strength <sup>10</sup> |               |                   | ISO 179/1eU              |
| -30°C                                          | No Break      |                   | ISO 179/1eU              |
| 23°C                                           | No Break      |                   | ISO 179/1eU              |
| Notched Izod Impact                            |               |                   |                          |
| -30°C                                          | 110           | J/m               | ASTM D256                |
| 0°C                                            | 330           | J/m               | ASTM D256                |
| 23°C                                           | 670           | J/m               | ASTM D256                |
| -30°C <sup>11</sup>                            | 10            | kJ/m <sup>2</sup> | ISO 180/1A               |
| 23°C <sup>12</sup>                             | 55            | kJ/m <sup>2</sup> | ISO 180/1A               |
| Unnotched Izod Impact Strength <sup>13</sup>   |               |                   | ISO 180/1U               |
| -30°C                                          | No Break      |                   | ISO 180/1U               |
| 23°C                                           | No Break      |                   | ISO 180/1U               |
| Instrumented Dart Impact                       |               |                   |                          |
| 23°C, Total Energy                             | 56.0          | J                 | ASTM D3763               |
| --                                             | 92.0          | J                 | ISO 6603-2               |
| Thermal                                        | Nominal Value | Unit              | Test Method              |
| Deflection Temperature Under Load              |               |                   |                          |
| 0.45 MPa, unannealed, 3.20mm                   | 124           | °C                | ASTM D648                |
| 1.8 MPa, unannealed, 3.20mm                    | 110           | °C                | ASTM D648                |
| 1.8 MPa, unannealed, 64.0mm span <sup>14</sup> | 120           | °C                | ISO 75-2/Af              |
| Vicat Softening Temperature                    |               |                   |                          |
| --                                             | 141           | °C                | ASTM D1525 <sup>15</sup> |
| --                                             | 135           | °C                | ISO 306/B50              |
| --                                             | 136           | °C                | ISO 306/B120             |
| Ball Pressure Test (125°C)                     | Pass          |                   | IEC 60695-10-2           |
| Linear thermal expansion coefficient           |               |                   | ASTM E831, ISO 11359-2   |
| Flow: -40 to 40°C                              | 8.0E-5        | cm/cm/°C          | ASTM E831, ISO 11359-2   |
| Lateral: -40 to 40°C                           | 8.0E-5        | cm/cm/°C          | ASTM E831, ISO 11359-2   |
| Optical                                        | Nominal Value | Unit              | Test Method              |
| Refractive Index                               | 1.582         |                   | ASTM D542                |
| Transmittance (2540 µm)                        | 88.0          | %                 | ASTM D1003               |
| Haze (2540 µm)                                 | < 1.0         | %                 | ASTM D1003               |

| Injection              | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature     | 104 - 110     | °C   |
| Drying Time            | 3.0 - 4.0     | hr   |
| Drying Time, Maximum   | 24            | hr   |
| Suggested Shot Size    | 40 - 60       | %    |
| Rear Temperature       | 238 - 282     | °C   |
| Middle Temperature     | 249 - 293     | °C   |
| Front Temperature      | 260 - 304     | °C   |
| Nozzle Temperature     | 254 - 299     | °C   |
| Processing (Melt) Temp | 260 - 304     | °C   |
| Mold Temperature       | 48.9 - 82.2   | °C   |
| Back Pressure          | 0.345 - 0.689 | MPa  |
| Screw Speed            | 35 - 75       | rpm  |
| Vent Depth             | 0.038 - 0.076 | mm   |

| NOTE |                           |  |
|------|---------------------------|--|
| 1.   | 5.0 mm/min                |  |
| 2.   | Type 1, 50mm/min          |  |
| 3.   | Type 1, 50mm/min          |  |
| 4.   | Type 1, 50mm/min          |  |
| 5.   | Type 1, 50mm/min          |  |
| 6.   | 1.3 mm/min                |  |
| 7.   | 2.0 mm/min                |  |
| 8.   | 1.3 mm/min                |  |
| 9.   | 80*10*3 sp=62mm           |  |
| 10.  | 80*10*3 sp=62mm           |  |
| 11.  | 80*10*3                   |  |
| 12.  | 80*10*3                   |  |
| 13.  | 80*10*3                   |  |
| 14.  | 80*10*4 mm                |  |
| 15.  | 标准 B (120°C/h), 载荷2 (50N) |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT