

RTP 1202-65D TFE 10

Thermoplastic Polyurethane Elastomer (Polyester)

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Additive	PTFE lubricant (10%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1380	MPa	ASTM D638
Tensile Strength	28.0	MPa	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength	34.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	370	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1300	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, Values per RTP Company testing.)	HB		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 6mil/in.			
Injection	Nominal Value	Unit	
Rear Temperature	182 - 210	°C	

Middle Temperature	182 - 210	°C
Front Temperature	182 - 210	°C
Mold Temperature	15.6 - 65.6	°C
Injection Pressure	68.9 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

