

Hifax TKC 220P G12761

Polypropylene Copolymer

LyondellBasell Industries

Message:

High Impact filled grade with very high scratch resistance.

General Information			
Features	High Impact Resistance		
	High Scratch Resistance		
	Medium Rigidity		
Uses	Automotive Bumper		
	Automotive Exterior Parts		
Appearance	Colors Available		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	95.0	°C	ISO 75-2/B
Vicat Softening Temperature	51.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT