

Sumikon® PM-5620

Phenolic
SBHPP

Message:

SUMIKON® PM-5620 (Type J Black) is Glass fiber and Graphite filled novolac resin molding compound with good wear resistance.

General Information	
Filler / Reinforcement	Glass fiber reinforced material
	Graphite fiber reinforced material
Features	Good wear resistance
RoHS Compliance	RoHS compliance
Appearance	Black
Forms	Powder
	Particles
Processing Method	Resin transfer molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.82	g/cm ³	JIS K6911
Molding Shrinkage - Flow	0.30	%	JIS K6911
Water Absorption (Equilibrium)	0.080	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength	114	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.3	kJ/m ²	JIS K6911

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT