

Alpha PVC FMPP

Flexible Polyvinyl Chloride

AlphaGary

Message:

ALPHAGARY PVC FMPP IS A FLEXIBLE COMPOUND DESIGNED FOR HIGH SPEED EXTRUSION OF COATED YARN USED IN THE CASUAL FURNITURE INDUSTRY. THIS MATERIAL WAS ENGINEERED TO WITHSTAND THE ABUSES OF OUTDOOR WEATHERING SUCH AS ULTRAVIOLET EXPOSURE AND ATTACK BY MOISTURE AND MILDEW. IT PROVIDES GOOD STRENGTH, ABRASION RESISTANCE AND LOW TEMPERATURE PROPERTIES. OTHER POSSIBLE APPLICATIONS INCLUDE WIRE FENCE COATING AND AUTOMOTIVE HARNESS CABLE COATING.

General Information			
Features	Good Abrasion Resistance		
	Good Strength		
	Good UV Resistance		
	Good Weather Resistance		
	Low Temperature Strength		
	Mildew Resistant		
	Moisture Resistant		
Uses	Coating Applications		
	Furniture		
	Yarn		
RoHS Compliance	Contact Manufacturer		
Appearance	Clear/Transparent		
	Colors Available		
	Grey		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 to 1.24	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, 6.35 mm)	80 to 86		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant (1.91 mm)	11.0	MPa	ASTM D638
Tensile Strength (1.91 mm)	17.9	MPa	ASTM D638
Tensile Elongation (Break, 1.91 mm)	250	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	59.5	kN/m	ASTM D1004
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	-27.0	°C	ASTM D746
Extrusion	Nominal Value	Unit	
Melt Temperature	166 to 177	°C	
NOTE			
1.	Graves		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT