

POLLITE 1001A

Polycarbonate
POLYROCKS CHEMICAL CO., LTD

Message:

POLLITE 1001A is a Polycarbonate (PC) product. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.

Characteristics include:

Flame Rated
Flame Retardant
Heat Resistant
Impact Resistant

General Information			
Features	Flame Retardant		
	High Heat Resistance		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
UL File Number	E253482		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	58.0	MPa	ASTM D638
Tensile Elongation (Break)	85	%	ASTM D638
Flexural Modulus	2200	MPa	ASTM D790
Flexural Strength	85.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	660	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	135	°C	
1.8 MPa, Unannealed	126	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-0		
	V-0		
3.00 mm	5VA		
Injection	Nominal Value	Unit	

Drying Temperature	120	°C
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	260 to 280	°C
Mold Temperature	80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

