Sinvicomp SRF3872

Rigid Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

SINVICOMP SRF3872 is a rigid polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by injection molding. The main characteristics of SINVICOMP SRF3872 are: impact resistance.

Typical application areas include:

Electrical/electronic applications

engineering/industrial accessories

General Information			
Features	Impact resistance, good		
Uses	Electrical components		
	Accessories		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38 - 1.42	g/cm³	ASTM D792
Congo Red (190°C)	30.0	min	BS 2782
Melt flow-190°C/21.6kgs	28g/10mins		ASTM D1238
modulus of elasticity-in Tension	2.50	GPa	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	76		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	50.0	МРа	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	2700	МРа	ASTM D790
Flexural Strength	73.0	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	86.0	°C	ASTM D1525

Typical temperature profile for SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP. Feeding zone: 160°CMixing zone: 160°C~170°CMetering zone: 170°C~180°CNozzle/Die Zone: 180°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

