

LNP™ LUBRICOMP™ DP003 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* DP003 is a compound based on Polycarbonate resin containing 15% PTFE/Silicone. Added feature of this material is: Wear Resistant.
Also known as: LNP* LUBRICOMP* Compound DL-4530
Product reorder name: DP003

General Information			
UL YellowCard	E121562-101282872		
Additive	PTFE + Silicone Lubricant (15%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.90 to 1.0	%	ASTM D955
Across Flow : 24 hr	1.0 to 1.2	%	ASTM D955, ISO 294-4
Flow : 24 hr	0.80 to 1.0	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.10	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.19	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2230	MPa	ASTM D638
--	2170	MPa	ISO 527-2/1
Tensile Strength			
Yield	49.0	MPa	ASTM D638, ISO 527-2
Break	42.7	MPa	ASTM D638
Break	41.0	MPa	ISO 527-2
Tensile Elongation			
Yield	5.6	%	ASTM D638
Yield	5.8	%	ISO 527-2
Break	35	%	ASTM D638
Break	41	%	ISO 527-2
Flexural Modulus			
--	1900	MPa	ASTM D790
--	1840	MPa	ISO 178
Flexural Strength			

--	75.8	MPa	ASTM D790
--	75.2	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.10		
vs. Itself - Static	0.26		
Wear Factor - Washer	42.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	280	J/m	ASTM D256
23°C ²	32	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	No Break		ASTM D4812, ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	28.4	J	ASTM D3763
--	61.5	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	128	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ³	129	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Transverse : -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	7.1E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	304 to 316	°C	
Front Temperature	310 to 321	°C	
Processing (Melt) Temp	299 to 316	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

