

Hostaform® MR130ACS

Acetal (POM) Copolymer

Celanese Corporation

Message:

Hostaform® acetal copolymer grade MR130ACS is a general purpose acetal with improved acid stabilization. Hostaform® MR130ACS demonstrates improved performance over standard acetals after intermittent exposure to acidic cleaners.

General Information			
UL YellowCard	E42337-480405		
Features	General		
Uses	General		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C)	1.7	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	62.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	11	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	30	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	ISO 179/1eA
23°C	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	140	kJ/m ²	ISO 179/1eU
23°C	150	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
Melting Temperature ¹	170	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	9.4E-5	cm/cm/°C	ISO 11359-2
Lateral	1.0E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20.0 - 30.0	°C	

Rear Temperature	170 - 180	°C
Middle Temperature	180 - 190	°C
Front Temperature	190 - 200	°C
Nozzle Temperature	190 - 210	°C
Processing (Melt) Temp	190 - 210	°C
Mold Temperature	80.0 - 120	°C
Injection Pressure	60.0 - 120	MPa
Injection Rate	Slow-Moderate	
Holding Pressure	60.0 - 120	MPa
Back Pressure	0.00 - 0.500	MPa

Injection instructions

Manifold Temperature: 190 to 210°C Zone 4 Temperature: 190 to 210°C Feed Temperature: 60 to 80°C

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

