GATONE™ 5300X

Polyetheretherketone

Solvay Specialities India Private Limited (SSIPL)

Message:

 $\mathsf{GATONE}^{\scriptscriptstyle\mathsf{TM}}\ 5300X\ is\ a\ \mathsf{Polyetheretherketone}\ (\mathsf{PEEK})\ \mathsf{material}.\ \mathsf{It}\ is\ \mathsf{available}\ \mathsf{in}\ \mathsf{Asia}\ \mathsf{Pacific},\ \mathsf{Europe},\ \mathsf{or}\ \mathsf{North}\ \mathsf{America}.$

Important attributes of GATONE™ 5300X are:

Chemical Resistant

Heat Resistant

Radiation (Gamma) Resistant

Wear Resistant

Typical applications include:

Aerospace

Engineering/Industrial Parts

Electrical/Electronic Applications

Plumbing/Piping/Potable Water

Printing Applications

General Information				
Features	Good Chemical Resistance			
	Good Thermal Stability			
	Good Wear Resistance			
	Hydrolysis Resistant Machinable			
	Uses	Aerospace Applications		
Aircraft Applications				
Electrical/Electronic Applications				
Fluid Handling				
Printer Parts				
Pump Parts				
Rotating Equipment				
Valves/Valve Parts				
Forms	Pellets			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.32	g/cm³	ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	4140	МРа	ASTM D638	
Tensile Strength	93.8	MPa	ASTM D638	
Tensile Elongation (Break)	40	%	ASTM D638	
Flexural Modulus	4140	MPa	ASTM D790	
Flexural Strength	150	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	

Notched Izod Impact	65	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

