

TECHNYL® 2411GF6 Bright

Polyamide 66
Solvay Engineering Plastics

Message:
Polyamide 66, 30% glass fiber reinforced, for injection molding

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Gears		
		Housings		
		Industrial Applications		
		Reflectors		
		Sporting Goods		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.38	--	g/cm ³	ISO 1183
Molding Shrinkage				Internal Method
Across Flow	0.80	--	%	
Flow	0.50	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.80	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	121	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Yield)	1950	--	MPa	ASTM D638
Tensile Elongation (Break)	2.0	--	%	ASTM D638
Flexural Modulus	9100	--	MPa	ASTM D790
Flexural Strength (Break)	270	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	120	--	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	255	--	°C	ASTM D648
Melting Temperature	262	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	2.5E-5	--	cm/cm/°C	ASTM D696

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	6.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	3.8	4.0	kV/mm	IEC 60243-1
Relative Permittivity	40.0	30.0		IEC 60250
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	600	600	V	
Solution B	500	500	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 to 3.20 mm)	HB	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
--	650	--	°C	
0.800 mm	650	--	°C	
Glow Wire Ignition Temperature (1.60 mm)	650	--	°C	IEC 60695-2-13
Oxygen Index	23	--	%	ISO 4589-2
Fire and Smoke F Index - I2, F3	2	--		NF F16-101
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	270 to 275		°C	
Middle Temperature	275 to 285		°C	
Front Temperature	285 to 295		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT