

Promyde® B33

Polyamide 6

NUREL, S.A.

Message:

Promyde® B33 is a Polyamide 6 grade of medium viscosity suitable for extrusion applications in general like high tenacity yarns, corrugated tubes and certain compounding applications.

General Information	
Features	Medium Viscosity
Uses	Compounding
	High Tenacity Flat Yarn
	Tubing
Processing Method	Compounding
	Extrusion

Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Apparent Density ¹	0.69	g/cm ³	Internal Method
Moisture Content ²	< 0.10	%	Internal Method
Relative Viscosity	3.21 to 3.41		ISO 1628
Chip Size ³	2.50	mm	Internal Method
Monomers	< 0.60	%	ISO 599

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	220	°C	ISO 3146

NOTE	
1.	NAPPA-059
2.	NAPPA-032
3.	NAPPA-045

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT