

Elastron® TPO T100.D42.N

Thermoplastic Polyolefin Elastomer

Elastron USA, Inc.

Message:

A hard, colorable thermoplastic polyolefin elastomer (TPO) material belongs to thermoplastic elastomer (TPE) family designed for general purpose applications.
Bondable to: PP, EVA, PE

General Information			
Features	Bondability		
	General Purpose		
	Good Colorability		
	High Hardness		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	42		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.90	MPa	
300% Strain	7.60	MPa	
Tensile Strength (Break)	12.0	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Tear Strength	73.0	kN/m	ASTM D624
Additional Information	Nominal Value		Test Method
Ozone Resistance - Stressed	No Cracks		ASTM D518
Injection	Nominal Value	Unit	
Suggested Max Regrind	20	%	
Rear Temperature	155 to 175	°C	
Middle Temperature	165 to 185	°C	
Front Temperature	175 to 195	°C	
Nozzle Temperature	195 to 225	°C	
Mold Temperature	25.0 to 50.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

