

LG ABS SH610S

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

Description
Excellent Surface, High Impact
Application
Bag, Miscellaneous

General Information			
Features	Impact resistance, good		
	Excellent appearance		
Uses	Bags		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	35.3	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield, 3.20mm	> 5.0	%	ASTM D638
Fracture, 3.20mm	35	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1960	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	56.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.20 mm	410	J/m	ASTM D256
23°C, 6.40 mm	350	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm ⁵	92.0	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm ⁶	87.0	°C	ASTM D648
Vicat Softening Temperature	94.0	°C	ASTM D1525 ⁷
Extrusion	Nominal Value	Unit	
Drying Temperature	70.0 - 80.0	°C	
Drying Time	3.0 - 4.0	hr	

Suggested Max Moisture	< 0.010	%
Cylinder Zone 1 Temp.	180 - 210	°C
Cylinder Zone 2 Temp.	190 - 230	°C
Cylinder Zone 3 Temp.	200 - 250	°C
Cylinder Zone 4 Temp.	200 - 250	°C
Adapter Temperature	200 - 250	°C
Melt Temperature	200 - 250	°C
Die Temperature	200 - 250	°C

Extrusion instructions

Top RollStack Temperature: 70 to 100°C Middle RollStack Temperature: 70 to 90°C Bottom RollStack Temperature: 60 to 90°C

NOTE

1.	50 mm/min
2.	50 mm/min
3.	15 mm/min
4.	15 mm/min
5.	4.6kg
6.	18.6kg
7.	速率 A (50°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

