T-Blend® 6594N-NL

Thermoplastic Elastomer

TSRC Corporation

Message:

T-Blend® 6594N-NL is a Thermoplastic Elastomer (TPE) product. It can be processed by extrusion or injection molding and is available in Asia Pacific. Applications of T-Blend® 6594N-NL include handles, bags/liners, business/office goods, consumer goods and engineering/industrial parts.

Characteristics include:

Chemical Resistant

Eco-Friendly/Green

Fast Molding Cycle

Food Contact Acceptable

Good Adhesion

General Information					
Features	Fast Molding Cycle				
	Food Contact Acceptable				
	Good Adhesion				
	Good Chemical Resistance				
	Good Colorability				
	Good Weather Resistance				
	Non-Toxic				
	Recyclable Material				
Uses	Flexible Grips				
	Household Goods				
	Liners				
	Overmolding				
	Power/Other Tools				
	Sporting Goods				
	Stationary Supplies				
	Toothbrush Handles				
	Toys				
Agency Ratings	FDA Food Contact, Unspecified Rating				
Appearance	Natural Color				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.880 to 0.920	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (180°C/5.0 kg)	20 to 50	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		

Durometer Hardness (Shore A)	63 to 67		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	4.41	MPa	ASTM D412
Tensile Elongation (Break)	450	%	ASTM D412
Tear Strength	24.5	kN/m	ASTM D624
Additional Information	Nominal Value		
Substrate	Nylon		
Injection	Nominal Value	Unit	
Processing (Melt) Temp	260 to 270	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

