

AKROMID® S3 GF 15 1 natural (3223)

Polyamide 610
AKRO-PLASTIC GmbH

Message:

AKROMID® S3 GF 15 1 natural (3223) is a 15% glass fibre reinforced, heat stabilised polyamide 6.10 with medium strength and stiffness, lower moisture absorption, high chemical resistance and light inherent color.
Applications are precision parts for apparatus engineering and precision mechanics as well as connectors, housings etc. in the automotive industry.

General Information				
UL YellowCard		E148915-102012843		
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Chemical Resistance		
		Good Stiffness		
		Heat Stabilized		
		Low Moisture Absorption		
		Medium Strength		
Uses		Automotive Applications		
		Connectors		
		Electrical Housing		
		Engineered Applications		
		Housings		
Appearance		Natural Color		
Resin ID (ISO 1043)		PA610 GF15		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.18	--	g/cm ³	ISO 1183
Spiral Flow	45.0	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	1.1	--	%	
Flow	0.60	--	%	
Humidity Absorption - 62% RH (70°C)	1.5	--	%	ISO 1110
Reinforcement Content	15	--	%	ISO 1172
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5000	3500	MPa	ISO 527-2/1
Tensile Stress (Break)	110	75.0	MPa	ISO 527-2/5
Tensile Strain (Break)	5.5	15	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	--	kJ/m ²	
23°C	5.0	--	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	--	kJ/m ²	
23°C	75	80	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	75.0	--	°C	ISO 75-2/C
Melting Temperature ¹	220	--	°C	DIN EN 11357-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ² (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
NOTE				
1.	10 K/min, DSC			
2.	> 1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

