

# KARIPRENE CREPE 6122/ 23-RTR

Thermoplastic Elastomer

Karina Ind. e Com. de Plásticos Ltda

Message:

THERMOPLASTIC RUBBER COMPOUND RECOMMENDED FOR SOLES INJECTION.

General Information			
Additive	Tin Stabilizer		
Uses	Footwear		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900 to 0.960	g/cm <sup>3</sup>	ASTM D792
Color	OK		ME 12
Abrasion Resistance	< 220	mm <sup>3</sup>	DIN 53516
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec	58 to 62		
Shore A, Injection Molded	62		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 4.90	MPa	ASTM D638
Tensile Elongation (Yield)	> 450	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT