

Paraclean® 28L35

Acrylonitrile Butadiene Rubber

INSA

Message:

Description:
"Clean" Low Volatility nbr for injection molding.
Fast Curing,
Excellent low temperature flexibility with moderate oil resistance.
Low water absorption.
Low corrosion.
Cold polymerized.
Non staining stabilizer.
Applications:
Injection molded products.
O-rings, seals, gaskets, grommets, and diaphragms.
Hose and tubes requiring low temperature flexibility.

General Information			
Features	Fast Cure		
	Good Processability		
	Low Temperature Flexibility		
	Low to No Water Absorption		
	Stain Resistant		
Uses	Diaphragms		
	Gaskets		
	Grommets		
	Hose		
	Seals		
	Tubing		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.970	g/cm ³	ASTM D297
Mooney Viscosity (ML 1+4, 100°C)	28 to 42	MU	ASTM D1646
ACN Content - Bound	26.5 to 29.5	wt%	Internal Method
Ash Content	< 0.8	wt%	ASTM D5667
Volatile Matter	< 1.0	wt%	ASTM D5668

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

