

LNP™ COLORCOMP™ HF1110RC compound

Polycarbonate

SABIC Innovative Plastics

Message:

COLORCOMP HF1110RC is a compound based on Polycarbonate resin. Added features include: High Flow, Mold Release. For use in thin wall lighting lenses, data storage components and safety eyewear lenses.

General Information			
Features	High liquidity		
	Good demoulding performance		
Uses	Lighting Applications		
	Lens		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	62.1	MPa	ASTM D638
Fracture	65.5	MPa	ASTM D638
Tensile Elongation ² (Break)	120	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	2310	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	640	J/m	ASTM D256
Instrumented Dart Impact (23°C, Energy at Peak Load)	54.2	J	ASTM D3763
Tensile Impact Strength ⁵	378	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	127	°C	ASTM D648
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value		Test Method
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 1		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2		UL 746

Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.1 mm)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (2540 μm)	88.0	%	ASTM D1003
Haze (2540 μm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	249 - 271	°C	
Middle Temperature	260 - 282	°C	
Front Temperature	271 - 293	°C	
Nozzle Temperature	266 - 288	°C	
Processing (Melt) Temp	271 - 293	°C	
Mold Temperature	71 - 93	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	Type 1, 50mm/min		
2.	Type 1, 50mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	Type S		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT