

# SABIC® PP 576S

Polypropylene Homopolymer

Saudi Basic Industries Corporation (SABIC)

## Message:

SABIC® PP 576S is a PP homopolymer grade that has good flow properties, excellent demoulding properties and a narrow molecular weight distribution. Products made from SABIC® PP 576S typically have low warpage, high stiffness in combination with moderate impact strength at room temperature and a high gloss.

SABIC® PP 576S is typically used in caps & closures and thin wall packaging both in food and non-food segments, and appliances.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/medical applications.

General Information			
UL YellowCard	E111275-306885		
Additive	Antistatic		
Features	Antistatic		
	Good Flow		
	Good Mold Release		
	Good Stiffness		
	High Gloss		
	Homopolymer		
	Low Warpage		
	Medium Impact Resistance		
Narrow Molecular Weight Distribution			
Uses	Appliances		
	Caps		
	Closures		
	Food Packaging		
	Packaging		
Thin-walled Packaging			
UL File Number	E111275		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.905	g/cm <sup>3</sup>	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Shore Hardness (Shore D)	71		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			

1% Secant <sup>1</sup>	1850	MPa	ASTM D638
--	1800	MPa	ISO 527-2/1A/1
<b>Tensile Strength</b>			
Yield <sup>2</sup>	37.0	MPa	ASTM D638
Yield	37.0	MPa	ISO 527-2/1A/50
<b>Tensile Elongation</b>			
Yield <sup>3</sup>	9.0	%	ASTM D638
Yield	9.0	%	ISO 527-2/1A/50
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength (23°C)	4.0	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Notched Izod Impact</b>			
23°C	25	J/m	ASTM D256A
23°C	3.0	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
<b>Deflection Temperature Under Load</b>			
0.45 MPa, Unannealed	95.0	°C	ASTM D648
0.45 MPa, Unannealed <sup>4</sup>	90.0	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	65.0	°C	ASTM D648
1.8 MPa, Unannealed <sup>5</sup>	60.0	°C	ISO 75-2/Af
<b>Vicat Softening Temperature</b>			
--	152	°C	ASTM D1525, ISO 306/A120 <sup>6</sup>
--	94.0	°C	ASTM D1525, ISO 306/B120 <sup>7</sup>
<b>NOTE</b>			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	testbar 80*10*4mm		
5.	testbar 80*10*4mm		
6.	Rate B (120°C/h), Loading 1 (10 N)		
7.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

