

EPDM 570

Hydrocarbon Rubber

The Dow Chemical Company

Message:

EPDM 570 is an amorphous ethylene-propylene-diene terpolymer (EPDM) grade designed for extruded applications. It is ideally suited for dense extruded profiles, coolant hoses, and general-purpose moldings. The combination of high viscosity and low crystallinity allows for good balance of processability, extensibility, low-temperature properties, and performance.

Main Characteristics:

- Amorphous
- Medium diene
- High molecular weight
- Good low temperature properties

Applications:

- Extruded profiles
- Coolant hoses

Notes:

Can be used in contact with all foods except water in oil emulsions, high or low fat, and low moisture fats and oil.

Adhesives only.

Complies with

- U.S. FDA 21 CFR 177.2600
- U.S. FDA 21 CFR 177.1520
- U.S. FDA 21 CFR 175.105
- U.S. FDA 21 CFR 177.1210

Consult the regulations for complete details.

General Information			
Agency Ratings	FDA 21 CFR 175.105		
	FDA 21 CFR 175.1520		
	FDA 21 CFR 177.1210		
	FDA 21 CFR 177.2600		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860	g/cm³	ASTM D297
Mooney Viscosity (ML 1+4, 125°C)	65 - 75	MU	ASTM D1646
Ethylene Content	49.0 - 51.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	4.5 - 5.3	wt%	ASTM D6047
Propylene content	45.0	wt%	ASTM D3900
Residual conversion metal		ppm	Internal method
Molecular Weight Distribution	Medium		Internal method
Ash Content	wt%		ASTM D5667
Volatile Matter	wt%		Internal method
Additional Information			

Storage and Handling:The quality of EPDM products may be affected by exposure to artificial or natural light. This product should be stored indoors in its original packaging and out of direct sunlight.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

