

Wellamid® NY1599-GY

Polyamide 66
Wellman Engineering Resins

Message:

Wellamid® NY1599-GY is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

General Information			
Features	General Purpose		
Uses	General Purpose		
Appearance	Grey		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	1.0 to 1.4	%	
Flow : 23°C	1.0 to 1.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	80.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	10	%	ISO 527-2
Flexural Modulus (23°C)	3000	MPa	ISO 178
Flexural Stress (23°C)	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	ISO 75-2/A
Melting Temperature (DSC)	260	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 282	°C	
Middle Temperature	260 to 277	°C	
Front Temperature	260 to 271	°C	
Nozzle Temperature	260 to 293	°C	
Processing (Melt) Temp	271 to 293	°C	
Mold Temperature	37.8 to 93.3	°C	
Injection Pressure	34.5 to 138	MPa	
Back Pressure	0.345	MPa	

Screw Speed

30 to 120

rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

