

DOW™ HDPE DMDA-8940 HEALTH+™

High Density Polyethylene Resin

The Dow Chemical Company

Message:

Dow HDPE DMDA-8940 HEALTH+™ Resin is a narrow molecular weight distribution high density copolymer designed to offer an excellent balance of toughness, environmental stress crack resistance, and processability. The resin is suitable for injection-molded medical devices such as IV kit components and respiratory care. This product can also be used in pharmaceutical packaging including caps and closures.

Main Characteristics:

Excellent toughness

Excellent stress crack resistance

Good processability

High gloss parts

Complies with:

U.S. FDA 21CFR 177.1520 (c) 3.2a

EU, No 10/2011

Canadian HPFB No Objection

USP XXIII Class VI

Drug Master File Listing

Consult the regulations for complete details.

General Information			
Agency Ratings	DMF not rated		
	FDA 21 CFR 177.1520(c) 3.2a		
	HPFB (Canada) No Objection		
	USP XXII, Class VI		
	Europe No 10/2011		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.951	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	44	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	26.9	MPa	ASTM D638
Fracture	26.9	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	5.0	%	ASTM D638
Fracture	10	%	ASTM D638
Flexural Modulus - 2% Secant	1020	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength ¹	84.1	kJ/m ²	ASTM D1822

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	71.1	°C	ASTM D648
Brittleness Temperature	< -72.2	°C	ASTM D746
Vicat Softening Temperature	123	°C	ASTM D1525
Melting Temperature (DSC)	128	°C	Internal method
Peak Crystallization Temperature (DSC)	116	°C	Internal method
Additional Information			
根据 ASTM D 4976 进行基板模制和测试.			
NOTE			

1. Type s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

