

DENIFORM 0037

Acetal (POM) Copolymer

Vamp Tech

Message:

POM, with elastomer, not Flame Retardant compound, very good impact resistance.

General Information			
Additive	Impact Modifier		
Features	Good Impact Resistance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Water Absorption (Saturation)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	900	MPa	ASTM D638
Tensile Strength (Yield)	35.0	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	18	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	°C	ASTM D648A
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	190	°C	
Mold Temperature	90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT