

TAFMER™ P-0680

Polyalphaolefin
Mitsui Chemicals America, Inc.

Message:
TAFMER™P-0680 is a polyα-olefin (PAO) material. This product is available in North America.
TAFMER™Typical application areas of P-0680 are: food contact applications

General Information			
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.870	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.40	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength	48	kV/mm	ASTM D149
Dielectric Constant	2.30		ASTM D150
Dissipation Factor	2.0E-4		ASTM D150
Additional Information			

Tensile Strength @ Break, JIS K 6301: 50 kgf/cm²Elongation @ Break, JIS K 6301: 950%Surface Hardness, JIS K 6301, A Scale: 63

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

