

ExxonMobil™ EnBA EN 33331

Ethylene n-Butyl Acrylate Copolymer Resin

ExxonMobil Chemical

Message:

ExxonMobil EN 33331 is a copolymer containing butyl 32.5% acrylate with high fluidity and is suitable for hot melt adhesives and sealants.

General Information			
Additive	heat stabilizer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	330	g/10 min	ASTM D1238
n-Butyl Acrylate Content	32.5	wt%	ExxonMobil Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	54		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1.31	MPa	ASTM D638
Tensile Elongation (Break)	98	%	ASTM D638
Flexural Modulus - 1% Secant	7.10	MPa	ASTM D790
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT