

Plenco 02571 (Compression)

Phenolic

Plastics Engineering Co.

Message:

PLENCO 02571 is a general purpose, organic filled phenolic molding compound offering optimum cure characteristics while maintaining excellent mechanical and electrical properties. UL recognized under component file E40654. 02571 is available in black or brown color.

General Information			
UL YellowCard	E40654-231591		
Filler / Reinforcement	Organic filler		
Features	Fast curing		
	Good electrical performance		
	General		
Uses	General		
UL File Number	E40654		
Appearance	Brown		
	Black		
Forms	Particles		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Apparent Density	0.62	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.48	%	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8290	MPa	ASTM D638
Tensile Strength	53.0	MPa	ASTM D638
Tensile Elongation (Break)	0.70	%	ASTM D638
Flexural Modulus	8470	MPa	ASTM D790
Flexural Strength	90.4	MPa	ASTM D790
Compressive Strength	212	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	19.1	J/m	ASTM D256
Notched Izod Impact	17	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648

Continuous Use Temperature	205	°C	ASTM D794
Thermal Conductivity (100°C)	0.37	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.0E+11	ohms·cm	ASTM D257
Dielectric Strength ¹	14	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.20		ASTM D150
Dissipation Factor (1 MHz)	0.047		ASTM D150
Arc Resistance	134	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Oxygen Index	26	%	ASTM D2863
Additional Information			
The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard.The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638.The value listed as Thermal Conductivity, ASTM C177 was tested according to the ASTM E1461 standard.Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.17%Heat Resistance, ASTM D794: 205°C Drop Ball Impact, PLENCO Method: 109 J/m			
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	0.50	hr	
Mold Temperature	165 - 182	°C	
Back Pressure	0.300	MPa	
Screw Speed	< 60	rpm	
Injection instructions			
Mold Close Time: 3-8 sec			
NOTE			
1. Method A (short time)			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT