

# Synthos PS GP 585X

General Purpose Polystyrene

Synthos S.A.

Message:

SYNTHOS PS GP 585X is general purpose polystyrene (GPPS) of excellent heat resistance and good rheological properties. It is a thermoplastic material designed for extrusion, thermoforming and injection moulding. Product has a form of cylindrical granules of diameter 2.5 to 6 mms. SYNTHOS PS GP 585X contains no internal lubricants.

APPLICATION

Injection moulding is used to produce parts with increased thermal resistance.

Production of XPS sheets and plates by means of direct extrusion and blowing.

It is suitable for blending with high-impact polystyrene (HIPS) and SBS copolymers to increase the thermal resistance of the product e.g. cups for hot drinks.

The composition of the polymer meets the requirements of the Health and can therefore be used for the production of articles coming into contact with food.

General Information			
Features	Food Contact Acceptable		
	General Purpose		
	High Heat Resistance		
Uses	Blending		
	Cups		
	General Purpose		
	Sheet		
Appearance	Colorless		
Forms	Granules		
Processing Method	Extrusion		
	Injection Molding		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	7.5 to 8.5	g/10 min	ISO 1133
Molding Shrinkage	0.20 to 0.50	%	Internal Method
Particle Size	2.50 to 6.00	mm	
Residual Styrene	0.020	%	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	9.0	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	99.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature		
Desiccant Dryer	80.0	°C
Hot Air Dryer	70.0	°C
Drying Time		
Desiccant Dryer	1.0	hr
Hot Air Dryer	2.0 to 4.0	hr
Processing (Melt) Temp	180 to 260	°C
Mold Temperature	10.0 to 60.0	°C
Extrusion	Nominal Value	Unit
Melt Temperature	200 to 240	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

