

YUPLENE® H230PL

Polypropylene Homopolymer
SK Global Chemical

Message:

YUPLENE H230PL is the homo polypropylene particularly suitable for Metallizable BOPP(Tender) film. H230PL is designed to combine the benefits of high speed grades with general purpose and metallizable grades.
H230PL meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact. H230PL has excellent processability and stretchability/High stiffness and strength/Good barrier properties, good optical properties, excellent metallizability.

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	Good Stretchability		
	High Stiffness		
	High Strength		
	Homopolymer		
	Metallizable		
	Opticals		
Uses	Film		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Clear/Transparent		
Processing Method	Bi-axially Oriented Film		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	36.3	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	155	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

