

ICORENE® PP CO14RM

Polypropylene Copolymer
ICO Polymers SA, A Division of A. Schulman

Message:

ICORENE® PP CO14RM is a Polypropylene Copolymer (PP Copolymer) product. It can be processed by rotational molding and is available in Latin America. Typical application: Food Contact Applications.

Characteristics include:

- Copolymer
- Food Contact Acceptable
- Good Processability
- Good UV Resistance
- Heat Resistant

General Information			
Additive	UV Stabilizer		
Features	Copolymer		
	Food Contact Acceptable		
	Good Processability		
	Good UV Resistance		
	High Heat Resistance		
	High Rigidity		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Natural Color		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.0	MPa	ASTM D638
Tensile Elongation ² (Break)	7.0	%	ASTM D638
Flexural Modulus ³	1350	MPa	ASTM D790
Aging	Nominal Value	Unit	Test Method
Accelerated Aging	5.5	month	ASTM G26
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT