## ELASTOSIL® P 7670 A/B

## Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, RTV-2

Orthopedic Products, Pharmaceuticals & Healthcare

General Information							
Features	Biocompatible BPA Free Breathable Good Chemical Resistance Good Flexibility Good Sterilizability Good Thermal Stability High Gas Permeability High Heat Resistance Low to No Odor Low to No Water Absorption						
					Non-Toxic		
					Steam Resistant		
				Uses	Medical/Healthcare Applications		
					Pharmaceuticals		
					Prosthetics		
				Uncured Properties	Nominal Value	Unit	Test Method
				Color	Translucent		
				Pot Life	20	min	
				Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	7		ISO 868				
Tensile Strength	1.80	MPa	ISO 37				
Tensile Elongation at Break	600	%	ISO 37				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Tear Strength

Susheng Import & Export Trading Co.,Ltd.

2.10

kN/m

ASTM D624B

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

