

Sumitomo Epoxy E 7459A

Epoxy; Epoxide

Sumitomo Bakelite North America, Inc.

Message:

EM 7459A is a medium strength fiberglass reinforced epoxy molding compound, which features enhanced impact strength and toughness.

General Information	
Filler / Reinforcement	Glass Fiber
Features	Good Impact Resistance
	Good Toughness
Appearance	Green
Forms	Flakes
Processing Method	Compression Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.73	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	115	MPa	ASTM D638
Flexural Strength (Break)	145	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	290	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT