

LAMINEX® 2140

Phenol Formaldehyde Resin

Schwartz Technical Plastic

Message:

Cotton fabric, phenolic resin impregnated, compression-moulded in moulds

Applications:

Bearing shells

Bearing collars

General Information			
Additive	Molybdenum disulfide lubricant		
Uses	Fabric		
	Bearing		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	130	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000 - 8000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	60.0	MPa	ISO 527-2
Fracture	80.0	MPa	ISO 527-2
Compressive Stress	150	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	18	kJ/m ²	ISO 180
Unnotched Izod Impact Strength	25	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	1.5E-5 - 3.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.30	W/m/K	ISO 8302
Additional Information			

Safe Temperature Range, short periods: 150°C Safe Temperature Range, permanent: 125°C Moisture Absorption under normal air condition: 450 mg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

