

Huaфон HF-1398A

Thermoplastic Polyurethane Elastomer (Polyester)

Huaфон Group Co., Ltd.

Message:

Operation: Extrusion, Blow molding, Blowing film
Characteristics: Excellent physical properties, Great transparency, Easy & stable process, stable processing point
Applications: Film, Cable, Tube, Conveyor belt, Elastic tape, Straps, Air-bag, Accessories, etc.

General Information	
Features	Good Processability
	High Clarity
Uses	Blown Film
	Conveyors
	Strapping
	Tape
	Tubing
	Wire & Cable Applications
Appearance	Clear/Transparent
Processing Method	Blow Molding
	Blown Film
	Extrusion

Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	57		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion	165	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	15.0	MPa	ASTM D412
Tensile Strength	33.0	MPa	ASTM D412
Tensile Elongation (Break)	480	%	ASTM D412
Tear Strength	205	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

